

Express Mail Certification

Date of Deposit: August 7, 2001

Mailing Label Number: EL569393835US

I hereby certify that this paper is being deposited pursuant to 37 CFR 1.10 with the United States Postal Service as "Express Mail - Post office to Addressee" on the above stated date under the above stated mailing label number in an envelope addressed to the Assistant Commissioner for Patents, Washington, D.C. 20231.

Patent#1894

Martin Crossman
James Rosie
Dan Solarek

5

COMPOSITIONS FOR CONTROLLED RELEASE

FIELD OF THE INVENTION

10

The present invention relates to biodegradable chemical compositions in which a chemical, particularly at least one oil well chemical, is adsorbed onto particulate starch, particularly granular starch, providing a stable, controlled release formulation suitable for use in oil field applications. The invention further relates to the process of preparing these compositions.

15

BACKGROUND OF THE INVENTION

The application of coating materials on various substrates is a well known technique for controlling or delaying the release of that substrate when

5 deteriorate. For example, the encapsulation of an oil well chemical intended to be
functional in a subterranean oil recovery operation insulates the chemical from
immediate contact with the environment into which it is introduced, thereby
maintaining the integrity of the chemical and preventing undesirable
agglomeration or reaction until the chemical may be released in the desired
10 location.

 A variety of chemical compositions are conventionally used as controlled
release agents in the food, cosmetic, paint, pharmaceutical, personal care,
household, and polymer and oil field industries. Conventional controlled release
compositions typically operate as encapsulating agents and include gum arabic,
15 dextrins, low viscosity modified starches, arabinogalactan, gum acacia, casein,
gelatin, carboxymethyl cellulose, tragacanth, karaya, sodium alginate, tannin, and
celluloses.

 Solubilized starches having been disclosed as agents for use in oil field
encapsulation technology. US Patent No. 4,704,214, for example, describes the
20 use of polysaccharides and polyols to form matrices for encapsulating various
ingredients, especially oil field chemicals. In this case, a polysaccharide, which
may be starch, is solubilized to form an inert film that surrounds an oil absorbent
polymer. The film subsequently melts or slowly dissolves, releasing the oil-
swelling polymer, which then closes off fractures or large pores without clogging
25 the borehole of the oil well. The encapsulation of a wide range of oil field
chemicals is also discussed in U.S. Patent No. 5,922,652 wherein a complex
colloid, which may be a gelatinized starch, forms a coacervate with water-
immiscible droplets of the chemical. U.S. Patent No. 5,546,798 discloses that

5 starch may be used as a water soluble thickening agent in conjunction with a swelling clay and a sealing agent such as calcium carbonate in order to encapsulate and thus preserve oil field core sample integrity. These forms of encapsulation all require the use of solubilized or non-particulate starch in their encapsulation formulation.

10 The use of particulates, both soft and hard, are also known controlled release ingredients for use in oil field applications. As discussed in U.S. Patent Nos. 5,560,439 and 5,204,183, typical particulates are calcium carbonate, clays, urea, polyvinyl acetate powder or emulsions. Particulates are often used as fillers or swelling agents in conjunction with water soluble thickening agents such as
15 polyethylene glycols, polyethylene glycol or a sulfonated elastomeric polymer. In particular, US Patent No. 5,628,813 describes the use of a lignosulfonate coating containing a particulate, such as talc, TiO_2 , silica, clays or gypsum which functions as a filler. The lignosulfonate coating is a secondary encapsulation intended to protect a thin, water permeable polymeric coating for encapsulating
20 pharmaceuticals, agricultural chemical and oil well chemicals. There remains a continuing need for a variety of controlled release agents that may be modified to suit a number of environments, particularly oil field applications.

Accordingly, it has now been discovered that particulate starch desirably adsorbs chemicals, thereby providing stable, controlled release chemical
25 compositions suitable for oil field applications.

5

SUMMARY OF THE INVENTION

The present invention relates to chemical compositions in which the chemical, particularly at least one oil well chemical, is adsorbed onto particulate starch. The particulate starch of the present invention includes granular starch and, resistant starch made therefrom, particularly granular starch.

10

The preparation of the present chemical compositions comprises mixing the chemical with the particulate starch. Adjuncts useful in controlled release formulations may optionally be added to the mixture. The mixture may also be optionally subjected to further treatment so that a stable, free-flowing chemical composition is obtained.

15

The chemical compositions of this invention are advantageously biodegradable and exhibit good controlled release properties, particularly in oil well applications.

20

DETAILED DESCRIPTION OF THE INVENTION

The present invention relates to controlled release chemical compositions in which the chemical, particularly at least one oil well chemical, is adsorbed onto particulate starch. The invention further relates to the process of obtaining these compositions and their method of use.

25

Use of starch as a carrier for the oil well chemical offers many advantages over those carriers generally used in the industry. For example, the starch is biodegradable and provides a good environmental profile.

5 The term starch particulate as used herein is intended to include starches with a highly organized structure, including granular starches and resistant starches made therefrom.

 All granular starches and flours (hereinafter "starch") may be suitable for use herein and may be derived from any native source. A native starch as used
10 herein, is one as it is found in nature. Also suitable are starches derived from a plant obtained by standard breeding techniques including crossbreeding, translocation, inversion, transformation or any other method of gene or chromosome engineering to include variations thereof. In addition, starch derived from a plant grown from artificial mutations and variations of the above genetic
15 composition, which may be produced by known standard methods of mutation breeding, are also suitable herein.

 Typical sources for the starches are cereals, tubers, roots, legumes and fruits. The native source can be corn, pea, potato, sweet potato, banana, barley, wheat, rice, sago, amaranth, tapioca, arrowroot, canna, sorghum, and waxy or
20 high amylose varieties thereof. As used herein, the term "waxy" is intended to include a starch containing at least about 95% by weight amylopectin and the term "high amylose" is intended to include a starch containing at least about 40% by weight amylose.

 Conversion products which retain their granular structure may be derived
25 from any of the starches, including fluidity or thin-boiling starches prepared by oxidation, enzyme conversion, acid hydrolysis, heat and or acid dextrinization, and or sheared products may also be useful herein.

5 Particularly useful are granular structures, which have been "pitted" by
the action of enzymes or acid, leaving a still organized structure which creates a
microporous starch. The enzymatic or acid hydrolysis of the starch granule is
carried out using techniques well known in the art. The amount of enzyme used is
dependent upon the enzyme, i.e., type, source and activity, as well as enzyme
10 concentration, substrate concentration, pH, temperature, the presence or
absence of inhibitors, and the degree and type of modification. Types of
modifications are described herein, *infra*. These parameters may be adjusted to
optimize the nature and extent of the "pitting" of the starch granule.

 Another particulate starch useful in the controlled release applications of
15 the present invention is resistant starch. Resistant starch is commonly known as
a starch not likely to be adsorbed in the small intestine of a healthy individual.
Granular or particulate starches, such as of the RS2-type (a starch granule that
resists digestion by pancreatic alpha-amylase) and the RS4-type (a chemically
modified starch, such as acetylated, hydroxyalkylated, or cross-linked starch) are
20 particularly suitable. However, resistant starches of the RS3-type (retrograded,
nongranular starch formed by heat/moisture treatment of starch) are also suitable
for the instant invention due to their high level of retrogradation or crystallization
from the alignment and association of associated amylose. In the case of an
RS3-type of starch, the order present in the original granular state has been
25 replaced with a crystalline order associated with retrograded amylose that may
swell a bit in water but doesn't completely solubilize.

 These types of resistant starch are well known in the art and may be
exemplified by that disclosed in US Patent Nos. US 5,593,503 which describes a

5 method of making a granular resistant starch; US Patent Nos. 5,281,276 and
5,409,542 which describe methods of making resistant starches of the RS3 type;
US 5,855,946 which describes a method of making a resistant starch of the RS4-
type; and U.S. Application Serial No. 60/157370, which describes the formation of
a very highly resistant starch. The methods for making the resistant starches are
10 described in the preceding references, the disclosures of which are incorporated
herein by reference.

The starch particulate, including granular and resistant starches, may be
modified by treatment with any reagent or combination of reagents which
contribute to the controlled release properties of the starch, provided the
15 modification does not destroy the particulate nature of the starch. Chemical
modifications are intended to include crosslinked starches, including crosslinking
the particulate starch with reactive polymers. Preferred reactive polymers include
starches modified with aldehyde or silanol groups. Other chemical modifications
include, without limit, acetylated and organically esterified starches,
20 hydroxyethylated and hydroxypropylated starches, phosphorylated and
inorganically esterified starches, cationic, anionic, nonionic, and zwitterionic
starches, and succinate and substituted succinate derivatives of starch.
Preferred modified starches are starch acetates having a degree of substitution
("DS") of about up to about 1.5, particularly those disclosed in US 5,321,132,
25 thereby improving compatibility with synthetic hydrophobic materials. Such
modifications are known in the art, for example in Modified Starches: Properties
and Uses, Ed. Wurzburg, CRC Press, Inc., Florida (1986). Another particularly
suitable modified starch is starch octenylsuccinate, aluminum salt.

5 Other suitable modifications and methods for producing particulate
starches are known in the art and disclosed in U.S. Patent No. 4,626,288 which is
incorporated herein by reference. In a particularly useful embodiment, the starch
is derivatized by reaction with an alkenyl cyclic dicarboxylic acid anhydride by the
method disclosed in U.S. Patent Nos. 2,613,206 and 2,661,349, incorporated
10 herein by reference, or propylene oxide, more particularly by reaction with
octenylsuccinic anhydride.

 In choosing a suitable starch, one skilled in the art would look to its ability
to absorb and carry the chemical without leakage. This is important as the
chemical must arrive at its destination and not be lost along the way. For
15 example, when an oil well chemical is used, the starch must carry the chemical
along the pipe or umbilical until it reaches the oil well. Thus, the starch must be
stable in a transport medium, such as an organic, aqueous, or MEG medium
used in the oil field industry.

 One skilled in the art would further look to the ability of the starch to
20 release the chemical at its destination. Particulate starches effectively achieve
this requirement. When the starch cooks out, it will release the adsorbed
chemical. As different starches have different gelatinization temperatures, the
starch may be chosen such that it will release its chemical at a selected
temperature desired in the particular application.

25 The particulate starches of the present invention, including granular
starch and resistant starch, may be combined with chemical reagents, oil well
chemicals in particular, to form the controlled release chemical compositions of
the present invention.

5 Oil well chemicals in accordance with this invention include, without limit, friction reducers, corrosion inhibitors, wax inhibitors, hydrate inhibitors, gel breakers, tracers, surfactants, scale inhibitors, antifoaming agents, demulsifiers, pour point depressants, biocides, drag reducers, antioxidants, hydrogen sulfide scavengers, oxygen scavengers, deoilers, and asphaltene inhibitors. Such
10 chemicals can be in either liquid or solid form.

Scale inhibitors is intended to include without limitation phosphates, phosphate esters and inorganic phosphates, and (co-polymers of acrylates, maleates and sulphonates. Corrosion inhibitors is intended to include without limitation amines and polyamines; biocides such as aldehydes or
15 halopropionamides. Oxygen scavengers is intended to include without limitation sodium bisulfite.

Other oil well reagents such as those disclosed in U.S. Patent No. 4,670,166, the disclosure of which is incorporated herein by reference, may also be suitable. Another category of oil well chemicals are the so-called breaker
20 reagents which are introduced with fracturing fluids into subterranean formations to lower the viscosity of the fracturing fluid. Examples of such breaker reagents include without limitation sodium and ammonium persulfate, alpha and beta amylases and glucosidases and similar reagents such as disclosed in U.S. Patent No. 4,506,734, the disclosure of which is incorporated herein by reference.

25 Particularly suitable oil well chemicals are corrosion inhibitors, wax inhibitors, gas hydrate inhibitors, and asphaltene deposition inhibitors. Corrosion inhibitors include without limit, non-quaternized long aliphatic chain hydrocarbyl N-heterocyclic compounds and mono- or di-ethylenically unsaturated aliphatic

5 groups. Wax inhibitors include, without limit, polymers such polyethylene, or a
copolymeric ester such as ethylene vinyl acetate copolymers, alpha olefin
maleate, fumarate polyesters, and vinyl acetate polymers. Gas hydrate inhibitors
may be any conventional hydrophilic hydrate inhibitor including, without limit,
methanol, ethanol, hydroxy ethers, glycols, and ammonium chloride, sodium
10 chloride or calcium chloride solutions. Asphaltene inhibitors include, without limit,
amphoteric fatty acids or a salt of an alkyl succinate.

The controlled release chemical compositions of the present invention
may optionally include additional adjuncts which improve controlled release or are
themselves encapsulated by other encapsulation mediums known in the art.
15 Possible adjuncts include, without limit, plasticizers, surfactants, fillers, chelating
agents, thickening agents, particulates and other typical controlled release
ingredients such as gelatin, gum arabic, zein, soy protein, and
copolymer/polymers such as polyethylene and polyvinyl chloride.

Starch allows the compositions of the present invention to be made by a
20 one-step adsorption process. The chemical compositions of the present
invention may be prepared by mixing the desired oil well chemical with a starch
particulate to form a mixture and stirring vigorously at ambient temperature and
pressure. The amount of shear to which the starch/chemical mixture is exposed
may need to be adjusted to ensure that the chemical is properly adsorbed onto
25 the particulate starch.

Typically, the ratio of oil well chemical to starch is from about 30:70 to
80:20, more particularly from 40:60 to 60:40. Where practicable, the oil field
chemical is first melted before adding the chemical to the starch particulate,

5 especially if it is a wax inhibitor that is solid at room temperature. Optionally, at least one encapsulation adjunct and/or solvent may be included in the formulation mixture. Further, weighting agents may be added to minimize gravity separation of the composition with the oil well medium.

10 The formulation mixture may also be optionally subjected to further treatment so that a stable, free-flowing powder having controlled release properties is obtained. After obtaining the free-flowing powder, the encapsulated chemical composition is then optionally milled to a desirable particle size diameter, preferably less than 20 microns. The particle size of the present invention should be large enough to inhibit inhalation and to prevent powdering
15 when handling.

Optional treatments for obtaining the controlled release chemical compositions of the present invention include, without limit, subjecting the formulation mixture to treatments such as vacuum batch thermal processing, roll compaction, fluid bed processing, spray drying and extrusion. These processing
20 treatments are well known to one of ordinary skill in the art. The processing conditions of the treatment should be limited to those that produce a chemical composition in which the starch retains its particulate structure.

The resultant chemical compositions are in the form of a biodegradable, non-sticky, free flowing powder having controlled release properties. Upon
25 release of the adsorbed chemical, the starch will be carried by the aqueous phase and discharged into the environment. In contrast, the use of a solubilized starch in the formulation mixtures produces a sticky mixture that is unsuitable for controlled release applications.

5 Selection of the starch controls the release profile. For example, a starch which breaks down more easily or under less severe conditions will release the starch more quickly. Typically, the uncooked starch breaks down at high temperature, and thus is released when introduced to an aqueous or organic carrier fluid, forcing the expulsion of the encapsulated material into the stream.
10 However, the starch may be formulated to release under other conditions to which it would be exposed.

 The present compositions protect then adsorbed material from that of the medium, e.g. oilwell fluids, with which it may not be compatible and/or soluble. The starch allows for two incompatible (or compatible) oil well chemicals to be
15 carried in a medium. The starch also enables a higher loading of oil well chemical down in one injection line than without the starch and allows potentially hazardous materials to be handled easily and safely, limiting exposure. Further, the adsorption may make it possible to use materials that would otherwise have a flashpoint too low to be able to be used offshore.

20 The free flowing powder has preferable handling characteristics to the liquids when being used offshore. The dispersion of granular starch will be much easier than a fine powder if there is a high surface tension, or phase boundary, between the carrier starch and the oil well medium and is robust enough to be able to stand the shear stresses that will be employed to mix the material in the
25 carrying medium. i.e. impellers.

 The following examples are presented to further illustrate and explain the present invention and should not be taken as limiting in any regard.

5 EXAMPLES

 The following oil field chemicals were used:

Corrtreat 2001-29, a solid, water soluble, amphoteric, betain-based surfactant for use as a corrosion inhibitor, commercially available from TR Oil Services

10 Corrtreat 2001-30, a solid, trimercaptotriazine-based corrosion inhibitor, commercially available from TR Oil Services

Hytreat 569, ethanediol 2-butoxyethanol propan-2-ol PV caprolactam for use as a kinetic hydrate inhibitor, commercially available from TR Oil Services

15 Hytreat A560, quarternary ammonium 2-butoxyethanol diisobutyl ketone for use as an anti-agglomerate hydrate inhibitor, commercially available from TR Oil Services

Scaletreat 2001-26, a solid, phosphate-based, water soluble scale inhibitor, commercially available from TR Oil Services,

Scaletreat 2001-28, a solid, polymer-based, water soluble scale and corrosion inhibitor, commercially available from TR Oil Services

20 Scavtreat 1020, a liquid, water miscible, triazine hydrogen sulphide scavenger, commercially available from TR Oil Services

Trosquat, a liquid biocide formulation, commercially available from TR Oil Services

25 Waxtreat 398 - a liquid, EVA wax inhibitor, commercially available from TROil Services

Waxtreat 7302 - a liquid, resin-based asphaltene/wax dispersant, commercially available from TR Oil Services

Example 1:

30 This example illustrates a method of preparing the biodegradable controlled release chemical compositions of the present invention.

 A granular starch (150 g, starch octenylsuccinate, aluminum salt, commercially available from National Starch and Chemical Company) was added to a pour point suppressant, XPC 3147C (50 g, Aldrich), which had been melted
35 at a temperature greater than 30 C. The mixture was stirred at ambient

5 temperature and pressure in a high shear disperser (Torrence, #785049) at 2000-4000 rpm. An additional 100 g of the granular starch was added to the mixture and stirred for two more minutes to form a fine, free-flowing powder.

Example 2:

10 This example illustrates that the chemical compositions of the present invention comprising a particulate starch are superior to chemical compositions prepared with a solubilized starch.

Solubilized starch (250 g of a beta-amylase treated, 3% octenyl succinic anhydride modified waxy corn starch) was added to XPC 3147C (50 g, Aldrich) which had been melted at a temperature greater than 30°C. The mixture was stirred at ambient room temperature and pressure in a high shear disperser (Torrence) at 2000-4000 rpm.

The resultant solid was sticky to the touch and, unlike the superior free-flowing powder of Example 1, was unsatisfactory for use as a controlled release chemical composition.

Example 3.

This example illustrates compositions of the present invention using water soluble oil well chemicals.

25 Water soluble solids were formulated with starch at a 1:1 ratio (50% loading on starch). The oil well chemical was solubilized in ambient water and homogenized for 1-2 minutes at 9000-10000 rpm (Silverson L4RT). The starch was then added to the solution and the mixture was further homogenized for 2-3 minutes at 9000-10000rpm, 20°C (Silverson L4RT). The mixture was spray dried (40% solids, 375°F inlet temperature, 225°F outlet temperature with a feed rate of 160ml/minutes and dual wheel atomization using Bowen Lab Model (30" x 36")) to produce a flowable, non-sticky composition.

- 5 a. The example was carried out using a scale inhibitor, Scaletreat 2001-28, as the oil well chemical and Vulca 90, a maize starch crosslinked with 1.5% epichlorohydrin on dry starch.
- b. The example was carried out using a corrosion inhibitor, Corrtreat 2001-29 as the oil well chemical and a starch acetate (1.5 DS) waxy maize starch.
- 10 c. The example was carried out using a scale inhibitor, Scaletreat 2001-26 as the oil well chemical and a microporous waxy maize starch which was digested using 0.3% glucoamylase on dry starch to achieve 15% digestion.

Example 4.

- 15 This example illustrates compositions of the present invention using water insoluble oil well chemicals.

Water insoluble solids were formulated with starch at a 1:1 ratio (50% loading on starch). The oil well chemical was added to a waxy maize starch modified with 3% octenyl succinic anhydride and converted to a water fluidity of 40, and the mixture was homogenized for 1-2 minutes at 9000-10000 rpm, 20°C (Silverson L4RT). Water was added to the emulsion and the mixture was further homogenized, 1 minute at 9000-10000 rpm, 20°C (Silverson L4RT). The starch was then added to the solution and the mixture was further homogenized, 1-2 minutes at 9000-10000 rpm, 20°C (Silverson L4RT). The mixture was spray dried (35% solids, 380°F inlet temperature, 230°F outlet temperature, 140-160ml/minutes with dual wheel atomization using Bowen Lab Model (30" x 36")) to produce a flowable, non-sticky composition.

- 30 a. The example was carried out using a wax inhibitor, Waxtreat 398 as the oil well chemical and a microporous waxy maize which was 30% digested with 0.3% glucoamylase, and modified with 3% octenyl succinic anhydride and crosslinked with 1% aluminium sulfate.

- 5 b. The example was carried out using an asphaltene inhibitor, Waxtrear
7302 as the oil well chemical and a microporous waxy maize starch modified
using 3% octenyl succinic anhydride, enzymatically treated using 0.3%
glucoamylase, to achieve 30% digestion.
- 10 c. The example was carried out using hydrogen sulphide, Scavtrear 1020 as the
oil well chemical and a high amylose corn starch, HYLON® VII starch,
commercially available from National Starch and Chemical Company.
- 15 d. The example was carried out using a kinetic hydrate inhibitor, Hytrear 569 as
the oil well chemical and a microporous (30% enzyme digested) waxy maize
starch modified using 3% octenyl succinic anhydride, enzymatically treated using
0.3% glucoamylase.
- 15 e. The example was carried out using an anti-agglomerated hydrate inhibitor,
Hytrear A560 as the oil well chemical and a cationic starch silanol, 0.3% Nitrogen,
0.4% silanol.

20 Example 5 – This example shows further compositions representative of the
present invention.

25 Starch was weighed out into a glass container. The oil well chemical was added
while mixing for 5 minutes and then mixed for an additional 5 minutes, or until
uniform using a Powerstat, Variable Autotransformer set at 80 (3PN168), Bodine
Electric Co, Speed reducer motor (NSE-12R).

- 30 a. Starch used was a 50:50 blend of sago and tapioca, DD and the oil well
chemical used was Waxtrear 398. The starch:chemical ratio used was
100:40 and the loading was 28.6%.
- 30 b. Starch used was a high amylose (70%) maize starch modified by 3% octenyl
succinic anhydride and 10% polyvinyl alcohol and the oil well chemical used
was Waxtrear 398. The starch:chemical ratio used was 100:80 and the
loading was 44.4%.

- 5 c. Starch used was enzyme converted (alpha amylase) maltodextrin and the oil
 well chemical used was Trosquat. The starch:chemical ratio used was
 100:38 and the loading was 27.5%.
- d. Starch used was enzyme converted (alpha amylase) maltodextrin and the oil
 well chemical used was Troscat. The starch:chemical ratio used was 100:38
10 and the loading was 27.5%.
- e. Starch used was a high amylose (70%) maize which was gelatinized,
 completely enzymatically debranched and retrograded and the oil well
 chemical used was Hytreat A560. The starch:chemical ratio used was
 100:24 and the loading was 19.3.

15

 While the invention has been described with particular reference to
certain embodiments thereof, it will be understood that changes and modifications
may be made by those of ordinary skill within the scope and spirit of the following
claims.